



Redco™ PTFE

PROPERTY	UNIT	ASTM or UL TEST	VIRGIN PTFE	CHEMICALLY MODIFIED PTFE	15% GLASS FILLED PTFE	25% GLASS FILLED PTFE	15% GLASS FIBRE +5% MOS2 FILLED PTFE	25% CARBON# FILLED PTFE	35% CARBON# FILLED PTFE
----------	------	-----------------	-------------	--------------------------	-----------------------	-----------------------	--------------------------------------	-------------------------	-------------------------

PHYSICAL									
DENSITY	gm/cc	ASTM D-792	2.1-2.2	2.15 - 2.2	2.23-2.24	2.24-2.25	2.23-2.24	2.12-2.14	2.11-2.13
WATER ABSORPTION	%	ASTM D-570	0	0	0.015	0.013	0.015	0	0

MECHANICAL									
TENSILE STRENGTH	kgf/cm2	ASTM D-638	210-350	325	150-225	125-200	150-220	120-155	110-140
ELONGATION AT BREAK	%	ASTM D-638	250-400	400-450	225-325	200-300	220-320	100-150	90-125
COMPRESSIVE STRENGTH	kgf/cm2	ASTM D-695	40-50	45-55	65-75	75-85	65-75	75-85	80-90
COMPRESSIVE MODULUS	kgf/cm2	ASTM D-695	4000	4500	6000	7000	6000	8400	8700
DEFORMATION UNDER LOAD									
A. 2 Hrs. 23°C 113 kg/cm2	% ASTM D-621	12	3.5	10	9	10	5	4	
B. 24 Hrs. 23°C 113 kg/cm2			15	5	12	11	12	7	6
C. PERMANENT			8	2.5	7.5	7	7.5	3.5	3
D. 2 Hrs. 150°C 113 kg/cm2			55	40	52	50	50	35	30
FLEXURAL STRENGTH	kgf/cm2	ASTM D-790	57	60	50	42	50	96	90
FLEXURAL MODULUS	kgf/cm2	ASTM D-790	3500-6300	7000	20000	16700	20000	11900	10500
IMPACT STRENGTH									
A. -200°C	cmkgf/cm2	ASTM D-256	9	9	9.25	9.5	9	8	9.5
B. +200°C			15	15	12-May	11	12	10	12
HARDNESS	Shore D	ASTM D-2240	60-65	60-65	65-70	70-75	62-68	70-75	72-80
COEFFICIENT OF FRICTION									
A. DYNAMIC P-7 kg/cm2 V-0.5 m/s		---	0.04-0.06	0.02-0.03	0.31-0.37	0.5-0.54	0.15-0.20	0.12-0.17	0.13-0.18
B. STATIC P-35 kg/cm2			0.05-0.08	0.04-0.06	0.01-0.12	0.11-0.13	0.08-0.01	0.09-0.11	0.01-0.12

THERMAL																
HEAT RESISTANCE AT ATM. PRESSURE	°C	---	-250 to +260	-250 to +260	-250 to +260	-250 to +260	-250 to +260	-250 to +260	-250 to +260							
THERMAL CONDUCTIVITY	10-4 cal cm S° C	cenco Fitch	6	6	8	9	9	13	14							
LINER THERMAL EXPANSION	% ASTM D-696	Axial	Ra-dial	Axial	Radial	Axial	Radial	Axial	Radial	Axial	Radial	Axial	Radial	Axial	Radial	
A. 30-150°C			1.5	1.5	1.5	1.5	1.5	1.0	1.5	0.7	1.5	1.0	1.2	1.0	1.1	0.9
B. 30-200°C			2.4	2.3	2.4	2.3	2.3	1.8	2.2	1.0	2.3	1.8	1.9	1.5	1.8	1.4
C. 30-250°C			3.4	3.6	3.4	3.6	3.3	2.2	3.2	1.4	3.3	2.2	2.7	2.4	2.5	2.3

ELECTRICAL									
DIELECTRIC STRENGTH	Kv/mm	ASTM D-149	24	30-35	16	12	16	2	2
VOLUME RESISTIVITY	ohm in	ASTM D-257	401	402	400	400	40.9	40.9	40.9
SURFACE RESISTIVITY	ohm	ASTM D-258	1015	1018	1015	1015	1015	107	107

Chemical Resistance : PTFE is chemically inert & unaffected by all known chemicals except molten or dissolved alkali metals - Sodium; Potassium; Rubidium; Cesium; Francium & Fluorine gas, certain fluorine compounds & complexes at elevated temperatures. Filled PTFE has inferior chemical resistance depending upon the particular filler.

Properties are of Soft - Amorphous carbon filled PTFE. Properties of Hard carbon fibre filled PTFE :

Improved compressive properties, Improved wear properties & hardness, Improved flexural strength, Slightly inferior tensile properties, Compared to Soft - Amorphous carbon filled PTFE.

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, whether alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products. For most recent technical information, phone in USA or in Canada.