

Redco™ SURE GLIDE

PROPERTY	TYPICAL VALUES	ASTM or UL TEST
PHYSICAL		
DENSITY, g/cm ³	0.932 - 0.960	ASTM D 792
HARDNESS, SHORE D	62 - 67	ASTM D 785
MECHANICAL		
TENSILE STRENGTH, psi	2700 - 2900	ASTM D 638
ELONGATION AT BREAK, %	300 ≥	ASTM D 638
IMPACT STRENGTH, ft-lbs/in	no break	ASTM D 256
IZOD DOUBLE NOTCHED	-25	ASTM D 256
CO-EFFICIENT OF FRICTION		
STATIC	0.12 - 0.15	
DYNAMIC	0.07 - .010	
WATER ABSORPTION		
nil		
LINEAR THERMAL EXPANSION	0.10 x 10 ³	ASTM D 696
TEMPERATURE		
OPERATING TEMPERATURE		
MAXIMUM CONTINUOUS, °F	180	
MELTING POINT, °F	275 - 280	ASTM 789

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, whether alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products. For most recent technical information, phone in USA or in Canada.