



Redco™ Acetal

HUGE INVENTORY OF SHEET AND ROUND BAR

- **EASILY MACHINED**
- **QUICK DELIVERY**
- **FDA APPROVED**
- **LARGE INVENTORY**

**S
T
O
C
K
E
D**

Redco™ Acetal brings together the benefits of strength, stiffness, a low coefficient of friction, and dimensional stability providing a versatile and easily machinable material that exceeds the life of many parts that are traditionally metal.

Suited for a variety of industries and applications, Redco™ Acetal acts as an electrical insulator, is FDA Approved for food applications, and is an excellent material for use in applications requiring close-tolerances.

To minimize delivery times and meet design configurations, Redwood Plastics and Rubber stocks a broad array of Redco™ Acetal sheet and round bar. Custom colors and sizes are also available upon request.

**Call Us Today to Ensure the Most Optimal Material is
Used for Your Application.**



CAN **1.800.667.0999**
USA **1.866.733.2684**

Properties

Property	Test Method	Units	Acetal Copolymer
			Unfilled Copolymer
Specific Gravity	ASTM-D792	---	1.40
Tensile Strength	ASTM-D638	psi	9,000-10,200
Tensile Elongation	ASTM-D638	%	30-60
Tensile Modulus of Elasticity	ASTM-D638	psi	400,000
Flexural Strength	ASTM-D790	psi	12,000
Flexural Modulus of Elasticity	ASTM-D790	psi	366,000
Compressive Strength	ASTM-D695	psi	15,000
Izod Notched Impact	ASTM-D256	ft.-lb./in.	1
Rockwell Hardness	ASTM-D785	M scale	M90

Machining Guidelines

- The highest possible cutting speed should be chosen.
- Optimum chip removal must be ensured so that the chips are not drawn in by the tool.
- The tools that are used must be very sharp. Blunt tools can cause extreme heat, which results in deformation and thermal expansion.
- The clamping pressures must not be too high as this would result in deformation of the workpiece and the clamping tool would leave marks in the workpiece.
- Because of the low degree of stiffness, the workpiece must be adequately supported on the machine table and should lie as flat as possible.
- Perfect, high quality surfaces can only be obtained when the machines operate with low vibration.

Custom Design and Fabrication

Redwood Plastics and Rubber has designed and fabricated a variety of solutions to shock, abrasion, noise, wear and friction to many industries, resulting in increased production, decreased maintenance costs and decreased down time, adding to your bottom line.



We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for results obtained by the application of this or the safety and suitability of our products, whether alone or in combination with other products. Users are advised to make their own test to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products. For most recent technical information, phone 360 225 1491 in USA or 604 607 6000 in Canada. Printed in Canada

