

		MOLDINGS				
		SHAPES	FILLER			
PROPERTY	ASTM or UL TEST	UNFILLED	GLASS FIBER	25% GRAPHITE POWDER	15% GRAPHITE POWDER	LAMI-NATES
<b>PHYSICAL</b>						
SPECIFIC GRAVITY	D792	1.34	1.9	1.45	1.51	1.95
SPECIFIC VOLUME (in <sup>3</sup> /lb)	D792	-	14.5	19.0	18.3	14.1
WATER ABSORPTION, 24h, 1/8-in thk (%)	D570	0.4	0.2	0.6	0.2	0.3
<b>MECHANICAL</b>						
TENSILE STRENGTH (psi)	D638					
AT 70°F		20,300	27,000	5,700	9,500	50,000
AT 480°F		16,000	23,000	3,600	5,500	35,000
ELONGATION (%)	D638	4	<1	<1	4.5	<1
FLEXURAL STENGTH (psi)	D790					
AT 70°F		29,700	50,000	12,800	16,000	70,000
AT 480°F		24,000	36,000	9,200	9,000	50,000
FLEXURAL MODULUS (105 psi)	D790					
AT 70°F		58.0	32.5	9	5.5	40
AT 480°F		44.0	24.2	7.5	3.7	32
IMPACT STRENGTH, IZOD (ft-lb/in OF NOTCH)	D256	1.4	17	0.25	0.8	13
HARDNESS, ROCKWELL M	D785	110	20	110	88	-
<b>THERMAL</b>						
THERMAL CONDUCTIVITY (Btu-in/hr-ft <sup>2</sup> - °F)	C177	1.53	3.48	11.3	6.0	2.2
COEFFICIENT OF LINEAR THERMAL EXPANSION (10-5 in/in- °C)	D696	2.8	24.2	3.4	4.7	1
DEFLECTION TEMPERATURE (°F)	D648					
AT 264 psi		680	660	550	680	660
<b>ELECTRICAL</b>						
DIELECTRIC STRENGTH (V/mil)	D149					
SHORT TIME, 1/8-in thk		700	500	-	250	625
DIELECTRIC CONSTANT	D150					
AT kHz		3.41	4.7	-	13.3	4.5
DISSIPATION FACTOR	D150					
AT 1 KHz		0.0038	0.003	-	0.006	0.015
VOLUME RESISTANCY (ohm-cm)	D257					
AT 73°F, 50% RH		1018	5x10 <sup>15</sup>	-	1014	6x10 <sup>14</sup>
ARC RESISTANCE (s)	D495		180	-	-	180
<b>FRictionAL</b>						
COEFFICIENT OF FRICTION	-					
AGAINST STEEL, PV=10,000		-	-	0.24	0.24	-

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, whether alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products. For most recent technical information, phone in USA or in Canada.