

METRIC

Property	Method	Unit	Virgin	Repro	Cross Linked	Static Reduced
Density	ASTM D 792	lbs/in ³ (g/cm ³)	0.033 (0.93)	0.034 (0.94)	0.033 (0.93)	0.033-0.034 (0.93 - 0.94)
Tensile Break	ASTM D 638	PSI (MPa)	6000 (41)	4200 (30)	5200 (36)	4,800 - 5,600 (33-39)
Elongation at Break	ASTM D 638	%	400	300	350	300 - 400
Flexural Modulus	ASTM D 790B	PSI (MPa)	120,000 (830)	111000 (765)	120,000 (830)	100,000 - 150,000 (690-1035)
Abrasion	Internal	Steel = 100	16	14	7	10
Compressive Strength	ASTM D695	PSI	3000	2800	-	-
IZOD Impact						
Notched	ASTM D 256A	ft.-lbs./in. (J/m)	No Break	No Break	No Break	No Break
Double- notched	Internal	ft.-lbs./in. (J/m)	26 (1400)	21 (1300)	23 (1240)	
Linear Coefficient of						
Thermal Expansion	ASTM D 696	°K-1	2 x 10-4	2 x 10-4	0.9 x 10-4	1.8 x 10-4
Coefficient of Friction						
Static	ASTM D 1894	Unitless	0.2	0.2	0.2	.20 - .25

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, whether alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products. For most recent technical information, phone in USA or in Canada.