

PROPERTIES	TEST METHOD	UNIT	TYPICAL VALUE
Density	ASTM D 792	g/m <sup>3</sup>	0.93
Hardness	ASTM D 785	R Scale	67
Recommended Operating Temperature			
Maximum Continuous		°F(°C)	180 (82)
Tensile Properties	ASTM D 638		
Maximum Strength		psi (MPa)	5200 (36)
Yield Strength		psi (MPa)	2800 (19)
Elongation at break		%	400
Flexural modulus	ASTM D 790	psi (MPa)	90,000 (622)
Izod Impact Strength at 23 °C		ft-lbs/in <sup>2</sup> (kJ/m <sup>2</sup> )	
Notched	ASTM D 256A		No Break
Double Notched	ASTM D 4020		38 (78)
Mean coefficient of linear thermal expansion per °C	ASTM D 696		1.6 x 10 <sup>-4</sup>
Coefficient of friction against Cr-plated steel at 23°C	ASTM D 1894	°C	
Static			.15
Dynamic			.10
Abrasion Index	Sand Slurry		7.5
Surface Resistivity	ASTM D 257	ohms	>10 <sup>16</sup>
Volume Resistivity	ASTM D 257	ohms-cm	>10 <sup>16</sup>

We cannot anticipate all conditions under which this information and our products, or the products of other manufacturers in combination with our products, may be used. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, whether alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each such product or product combination for their own purposes. Unless otherwise agreed in writing, we sell the products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products. For most recent technical information, phone in USA or in Canada.